


Waveguide Loss



$$\text{Confinement factor} \quad \Gamma = \frac{\int_{\text{core}} |u(x,y)|^2 dx dy}{\int_{\text{all space}} |u(x,y)|^2 dx dy}$$

roughness
at waveguide
core/cladding
interface leakage
out of a
curved
waveguide

absorption
within core (Γ)
or within
cladding ($1-\Gamma$)

evanescent
leakage
to Si substrate

$$\alpha = \alpha_{\text{scattering}} + \alpha_{\text{radiative}} + \Gamma \alpha_{\text{abs,core}} + (1 - \Gamma) \alpha_{\text{abs,cladding}} + \alpha_{\text{substrate}}$$

$$\begin{aligned} P(z_0) &= \int |U(x,y)e^{-i\beta z_0} e^{-\alpha z_0/2}|^2 dx dy = \left\{ \int |U(x,y)|^2 dx dy \right\} e^{-\alpha z_0} \\ &= A e^{-\alpha z_0} \\ P(z_0 + L) &= A e^{-\alpha(z_0 + L)} \\ \text{Loss} &= \frac{P(z_0 + L)}{P(z_0)} = e^{-\alpha L} \end{aligned}$$

$$\begin{aligned} -\alpha L (\text{dB}) &\equiv 10 \log \left(\frac{P_{\text{out}}}{P_{\text{in}}} \right) \\ &= 10 \log(e^{-\alpha L}) \\ &= -\alpha L \cdot 10 \log(e) \end{aligned}$$

$$\begin{aligned} \alpha L (\text{dB}) &\cong 4.34 \cdot \alpha L \\ \alpha (\text{dB/cm}) &\cong 4.34 \cdot \alpha (\text{cm}^{-1}) \end{aligned}$$